

Your Company Name here

Your Address

Your City, Your State zip

Your Phone #

CLIENT : Your Client  
PROJECT : Project

ONE CUBIC YARD  
BATCH WEIGHTS

Report # 1

Mix # 1

Date: 3/3/2007

Comments:

Choose any quantity to see total weight of each component used such as 100 cubic yards or 0.10 cubic feet.

4000 psi Design Strength

Cement :	_____	373.3 lbs or	3.97 Sacks
Pozzolan #1:	_____	160.0 lbs or	1.70 Sacks
Pozzolan #2:	_____	0 lbs or	_____ Sacks
Coarse Agg:	_____	1,783.0 lbs	5.67 Total Sacks
Fine Agg:	_____	1,291.2 lbs	
Water:	_____	266.7 lbs or	32.0 Gallons
Design Slump (Inches):	_____	4.0 Inches	
Water Cement Ratio (lbs/lb):	_____	.50	
Entrained Air:	_____	3.0 %	
Admix #1:	_____	5.3 ounces	Air Ent
Admix #2:	_____	21.3 ounces	WR
Admix #3:	_____	53.3 ounces	HRWR
		3874.2 lbs/cu yd	
		143.5 lbs/cu ft	

Absolute Volume (Cubic Feet)

Cement :	1.8992
Pozzolan #1:	1.0684
Pozzolan #2:	0
Coarse Agg:	10.9901
Fine Agg:	7.9583
Water:	4.2740
Entrained Air:	0.8100