

Your Company Name here

Your Address

Your City, Your State zip

Your Phone #

CLIENT : Your Client

PROJECT : Project

ONE CUBIC METER

BATCH WEIGHTS

Report # 1

Mix # 1

Date: 3/3/2007

Comments:

Choose any quantity to see total weight of each component used such as 100 cubic yards or 0.10 cubic feet.

27.6 Mpa Design Strength

Cement :	_____	221.6 Kgs	or	3.97 Sacks
Pozzolan #1:	_____	95.0 Kgs	or	1.70 Sacks
Pozzolan #2:	_____	0 Kgs	or	_____ Sacks
Coarse Agg:	_____	1,058.3 Kgs		5.67 Total Sacks
Fine Agg:	_____	766.4 Kgs		
Water:	_____	158.3 Kgs	or	158 Liters
Design Slump (millimeters):	_____	102 mm		
Water Cement Ratio (Kg/Kg):	_____	.50		
Entrained Air:	_____	3.0 %		
Admix #1:	_____	0.21 liters		Air Ent
Admix #2:	_____	0.83 liters		WR
Admix #3:	_____	2.06 liters		HRWR

2,299.5 Kg/Cubic Meter

Volumetric Absolute

Cement :	0.0703
Pozzolan #1:	0.0396
Pozzolan #2:	0
Coarse Agg:	0.4070
Fine Agg:	0.2948
Water:	0.1583
Entrained Air:	0.0300